

2. (Amended) The process of claim 1, wherein the transalkylation catalyst comprises a mixture of at least:

- B1
- (i) a first crystalline molecular sieve having a X-ray diffraction pattern including d-spacing maxima at  $12.4 \pm 0.25$ ,  $6.9 \pm 0.15$ ,  $3.57 \pm 0.07$  and  $3.42 \pm 0.07$  Angstrom; and
  - (ii) a second crystalline molecular sieve different from the first molecular sieve and selected from zeolite beta and mordenite.

10. (Amended) A process for producing a monoalkylated aromatic compound comprising the steps of:

- B2
- (a) contacting an alkylatable aromatic compound with an alkylating agent in the presence of an alkylation catalyst to provide a product comprising said monoalkylated aromatic compound and a polyalkylated aromatic compound, and then
  - (b) contacting the polyalkylated aromatic compound from step (a) with said alkylatable aromatic compound under at least partial liquid phase conditions and in the presence of a transalkylation catalyst to produce a monoalkylated aromatic compound, wherein the transalkylation catalyst comprises a mixture of at least:
    - (i) a first crystalline molecular sieve having a X-ray diffraction pattern including d-spacing maxima at  $12.4 \pm 0.25$ ,  $6.9 \pm 0.15$ ,  $3.57 \pm 0.07$  and  $3.42 \pm 0.07$  Angstrom; and
    - (ii) a second crystalline molecular sieve different from the first molecular sieve and selected from zeolite beta, zeolite Y and mordenite.

*B3*  
~~15. (Amended) The process of claim 10, wherein the transalkylation catalyst comprises a mixture of at least:~~

- ~~(i) a first crystalline molecular sieve having a X-ray diffraction pattern including d-spacing maxima at  $12.4 \pm 0.25$ ,  $6.9 \pm 0.15$ ,  $3.57 \pm 0.07$  and  $3.42 \pm 0.07$  Angstrom; and~~
- ~~(ii) a second crystalline molecular sieve different from the first molecular sieve and selected from zeolite beta, and mordenite.~~

*B4*  
~~19. (Amended) A process for producing cumene comprising the steps of:~~

- ~~(a) contacting benzene with propylene under at least partial liquid phase conditions and in presence of an alkylation catalyst to provide a product comprising cumene and polyisopropylbenzenes, and then~~
- ~~(b) contacting the polyisopropylbenzenes from step (a) with benzene under at least partial liquid phase conditions and in the presence of a transalkylation catalyst to produce further cumene, wherein the transalkylation catalyst comprises a mixture of at least:~~
  - ~~(i) a first crystalline molecular sieve having a X-ray diffraction pattern including d-spacing maxima at  $12.4 \pm 0.25$ ,  $6.9 \pm 0.15$ ,  $3.57 \pm 0.07$  and  $3.42 \pm 0.07$  Angstrom; and~~
  - ~~(ii) a second crystalline molecular sieve different from the first molecular sieve and selected from zeolite beta, zeolite Y and mordenite.~~

A marked-up version of the existing claims 1, 2, 10, 15 and 19 showing the changes incorporated in the amended claims is attached on a separate sheet.